



DFP-GUN(spray gun for dry spray) Operation Manual

Thank you very much for buying our product.

DFP-GUN is an exclusive gun for dry painting for STELLA hologram flakes.

Dry painting is a method which is a spray flake powder as it is directly not to mix flake with clear.

DFP-GUN is available for not only STELLA but also any flake powder.

The caliber size of an ordinal spray gun (mixing with clear) had better 2.0mm to spray flake that size is ~ 0.4 mm.

However we need to dry spray if the flake size is more than 0.4mm.

The lineups of STELLA hologram flakes are from 0.05mm to 2mm and more than 0.6mm sizes need to be dry sprayed.

For example,

The STELLA sizes of 0.05mm, 0.1mm, 0.2mm, 0.4mm are available for ordinal spray (mixed with clear)

0.6mm, 1mm, 1.5mm, 2mm(2mm is from SSLH20) should be dry prayed by the DFP-GUN.

Open the cap of STELLA and put DFP-GUN. See "picture:2"

Flakes (which sizes tend to be big) are sometimes hard to be dry sprayed by DFP-GUN because of the air circulation.

Take off the center hose of DFP-GUN and spry again when it happens. See "picture:3"



picture:2



picture:3



Spray Process

- Spray clear (no hardener or hardener) after spray base color.
- Dry Spray flakes by DFP-GUN under wetting base color condition. (Spry gently at the first spray and learn it.)
- Spray clear and flakes again when you need more flakes' glitter.
- Finish dry spray flakes and topcoat clear after the glitter comes out perfectly.

Signal Inc., SHOW UP Division 2-6-8 Aoshinke Mino Si Osaka, Japan 562-0024 Tel. 072-727-7123 Fax. 072-727-2678 Email. info@showup.jp